

PROFESSIONAL FAST ADHESIVE

1 – DESCRIPTION

Professional Fast Adhesive is an adhesive set which consists of high viscosity cyanoacrylate adhesive and activator.

2 - PROPERTIES

- High bonding strength.
- Suitable for use on vertical surfaces as it will not drip or slump.
- It is particularly suited to bonding difficult substrates which have a porous or uneven nature since it increases bonding strength by preventing the adhesive to be absorbed by the surface.

3 - APPLICATIONS

- It is suitable for the bonding of a very wide range of materials, including acidic surfaces and some porous ones, where rapid bonding times are required.
- Suitable for MDF, wood, chip wood, rubber, most plastics, leather and other common substrates.
- Especially suitable for the applications where cure speed needs to be accelerated.
- Although it has a degree of gap filling ability, it is generally recommended for use on close-fitting parts and fairly smooth, even surfaces.

4 - INSTRUCTIONS

Substrates need to be smooth and have a perfect connection area. Apply a drop on one of the substrates. Join substrates and press firmly for one minute. Application temperature is between +5°C and +35°C.

5- PACKAGING

Product	Volume/Weight (Net)	Package
Activator & Glue	200 ml + 50 gr	24
Activator & Glue	400 ml + 100 gr	24

6- STORAGE AND SHELF LIFE

12 months in unopened packaging in a dry and cool storage place at temperatures between +5°C and +25°C.

7- SAFETY

- Cyanoacrylates should ideally be stored in original sealed containers until used.
- Avoid exposure to strong light and heat sources
- Cyanoacrylates can bond to skin within seconds

- Do not drip into skin or into eyes - can cause serious injury to your eyes.
- Will become hard in container if not closed properly!
- Activator is flammable. Do not throw into fire. Do not inhale.
- Activator box is pressured. Do not crush or drill.

8- TECHNICAL PROPERTIES

Glue

Basis	: Ethyl Cyanoacrylate
Appearance	: Liquid gel
Color	: Colorless
Application Temperature	: +5°C to +35°C
Density	: 1.06 ± 0.01 gr/cm ³ ASTM D1875
Flashpoint	: > 81 ° C
Viscosity	: 1200 - 1800 Cps at 25°C ASTM D1084
Temperature Resistance	: -20°C to +70 °C

Activator

Basis	: Hexane
Appearance	: Aerosol
Color	: Colorless
Application Temperature	: +5°C to +35°C
Temperature Resistance	: -20°C to +70 °C